



ALKYD

MEGALAC™ ALUMINUM

PRODUCT INFORMATION

PRODUCT DESCRIPTION Alkyd Megalac™ Aluminum is a general-purpose aluminum paint base on alkyd drying resins.

INTENDED USES A one pack aluminum finish coat suitable for both maintenance and new construction applications.

PRODUCT INFORMATION

Color	ATA002 - silver aluminum
Finish/Sheen	Not Applicable
Part B (Curing Agent)	Not Applicable
Volume Solids	26% (ISO 3233:1998)
Mix Ratio	Not Applicable
Typical Film Thickness	15-25 microns dry (57-95 microns wet)
Theoretical Coverage	17.33 m ² / L at 15 microns dft and 10.40 m ² / L at 25 microns dft
Method of Application	Brush, Roller, Conventional Spray, Airless Spray
Flash Point	33°C
Induction Period	Not Applicable

APPLICATION DETAILS

Mixing	Material is supplied in one pack container. Mix the supplied pack using a power agitator.	
Thinner	Not recommended; Use ENAMEL THINNER MTC 201 max. of 5% by volume when necessary	
Airless Spray	Recommended	Tip range 13-19 thou. Total output fluid pressure above 141 kg/cm ² (2010 psi)
Conventional Spray	Recommended	
Brush	Recommended	
Roller	Recommended	

DRYING INFORMATION

	28°C	32°C
Touch Dry (ISO1517:73)	4 hours	3 hours
Hard Dry (ISO9117:90)	36 hours	30 hours
Pot Life	Not Applicable	Not Applicable

OVERCOATING DATA - See limitations



ALKYD

MEGALAC™ ALUMINUM

SYSTEMS AND COMPATIBILITY

Recommended Primer – Megaprime™

STORAGE AND HANDLING

The product can be stored in sealed containers at 28 °C for a minimum of one year. Store in dry, shaded conditions, and away from sources of heat and ignition.

SURFACE PREPARATION

New Construction and Maintenance

The surface to be overcoated must be clean, dry and free from contamination (oil, grease, salt, etc.). Oil and grease should be removed in accordance with SSPC-SP 1 solvent cleaning. Dry bristle brushing will normally be adequate for cleaning. Damaged or corroded areas should be prepared to the specified standard and patch primed with Megaprime materials.

LIMITATIONS

When applying Aluminum Alkyd Enamel by brush or roller or if a light color is being used, two coats may be required to achieve a uniform color.

SAFETY PRECAUTIONS

Avoid contact with skin and eyes use proper equipment when handling material (i.e. gloves, goggles, face mask, barrier creams, etc.) Wash affected skin with lukewarm water and soap or suitable industrial cleaner. If you come contact with your eyes, flush your eyes with water for at least 10 minutes and seek immediate medical attention.

Important Note

The details in this data sheet are not meant to be comprehensive. Megapaint is not liable for any use of the product that is not specifically recommended in the datasheet without written permission. Any warranty, if given, or specific Terms & Conditions of Sale are contained in Megapaint's Terms & Conditions of Sale. The recommendations and remarks in this datasheet and by representatives regarding this product are accurate to the best of our understanding, but we cannot assure outside factors such as the quality of substrate when applying our product. Thus, we are not responsible for any damage except in cases where there is written agreement regarding the use of our product. The details in this data sheet are subject to change without prior notice due to alterations brought about by local laws or improvement of our product.

All trademarks mentioned in this publication are owned by, or licensed to, Megapaint Corporation

www.megapaint.com.ph